

Average Weight Pressures - Values in kg.						
Battens Length	18mm Hard	15mm Hard	15mm Medium	12mm Medium	18mm Carbon Nacra F20 C	15mm Carbon Nacra F20 C
260	2.1	1.4				
240	1.9	1.6				
220	1.9	1.8				
200	1.9	1.5				
180	2.2	1.8				
160	2.5	2.0	1.5	1.2		
145					6.0	4.3
140		2.4	1.8	1.4		
120		3.0	2.2	1.7		
100		3.4	2.7	2.2		
90		4.0	3.0	2.4		
80		4.8	3.4	1.9		
	Average of 5 battens in stock, measured April 2020. Indicative value cannot be used as a reference.					
	Moyennes de 5 lattes en stock, mesures Avril 2020. Valeurs indicative ne pouvant pas être utilisées comme valeur de références.					